

Coping Spray Paint

TECHNICAL BULLETIN (09/27/18)

The coping around the top of a pool is typically very durable, but it can discolor and age thereby diminishing the appearance. COPING SPRAY PAINT will brighten, restore the appeal and protect the existing coping material.





- Durable protective epoxy coating
- Non-slip; White Gloss Finish
- Easy spray application
- Resistant to fading & discoloration
- · Adheres well to virtually all surfaces
- VOC compliant

PHYSICAL DATA

RESIN TYPE: Alkyd

PIGMENT TYPE: Titanium Dioxide

Solvents: Mineral Spirits

MIR: E Volume—2.05/Colit Volume 1.20

FINISH: Gloss/Non-Slip COLORS: White COMPONENTS: 1 Fill Weight: 12 oz.

CURING MECHANISM: Air Dry

SOLIDS (theoretical):

By weight... By volume...

COVERAGE: Approximately 25 sq.ft/unit MIR: 2.05 EPA/1.20 CA g/l max. (as supplied)

FLASH POINT: > 155 °F (104° C)

SHELF LIFE: 2 Years

APPLICATION DATA

METHOD: Aerosol Spray NUMBER OF COATS: 2

DRY FILM THICKNESS PER COAT: 0.5 mils

APPLICATION TEMP: 50° F. Min. / 90° F. Max.

DRY TIME: @ 70°

To Re-Coat, dry to touch: 24 hours Before contact with water: 24 hours Allow more time in cooler temperatures or

humid conditions.

If rain occurs during curing process, allow and extra day of dry time for each day of rain.

Surfaces for Application: Concrete, Fiberglass, Vinyl, Plastic, Plaster, Marcite, Gunite, Steel,

and Painted Surfaces

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Coping Spray Paint

APPLICATION INFORMATION

Before you paint: Surface should be free of debris, chipping or peeling paint, grease, oil salt or contaminants. Apply 2 -inch wide painter's tape along the edge of the coping to protect nearby surfaces from over-spray.

Application: Ideal air temperatures for application are between 50°-90° F. Surface temperatures should be at least 50° and no more than 90°F. If surface temperatures are over 90°, consider painting early in the morning or at night. Overnight drying temperatures MUST be at least 50°F. Do not paint when rain is imminent. If rain occurs during the drying process allow an extra day of dry time for each day of rain.

Shake can vigorously for 1 minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Shake often during use. Apply Coping Spray Paint at the recommended coverage rate, holding can 10-16" from the surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Maintain even distance from the surface. Keep the can in motion while spraying. Dry time 24 hours between coats.

Applying two coats in one day or applying excessively heavy layers will lead to insufficient drying of the paint and soft or sagging paint film will result. Do not apply paint on extremely humid days (and over 90°) or when rain is threatening. When working in cooler temperatures be sure the air and surface temperatures will remain at or above 50°F for at least 8 hours after application.

Remove painter's tape within 24 hours of applying the final coat of paint. Avoid using the pool for 24 hours following the paint application to avoid splashing water onto your freshly painted coping.

Clean Up: Wipe off tip before storing. Properly discard empty container. Do not burn or place in home trash compactor. If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.